

## PRODUCT DATA SHEET

# SikaShield® P55 PE RT 4 mm

Anti-root plastomeric bituminous membrane surfaced with PE foil and flexible at -15 °C

### DESCRIPTION

SikaShield® P55 PE RT 4 mm is an APP modified bituminous waterproofing membrane with a thickness of 4 mm. It contains an anti-root additive, which allows the membrane to be in direct contact with the soil. It is reinforced with a non-woven polyester fabric dimensionally stabilised with glass fibre and is flexible at -15 °C. The top surface is coated with a polyethylene foil, which ensures the bond of the overlying layer. The underside of the product has a burn-off film for easy torch-application.

### USES

The Product is used as a waterproofing membrane for:

- Flat and sloping roofs under protective layers or ballast
- Inverted roofs
- Roof gardens
- Roof garden with final waterproofing layer in contact with soil
- Basements and other below ground structures
- Horizontal reinforced concrete slabs, decks, podiums and protrusions
- Vertical reinforced concrete walls

The Product is used as a:

- Base sheet in multi-layer systems
- Single layer under heavy protection

Please note:

- The Product is not suitable for roofs permanently exposed to UV radiation.

### PRODUCT INFORMATION

#### Composition

#### Composition

APP modified bitumen with anti-root additive

#### Reinforcing material

non-woven polyester fabric dimensionally stabilised with glass fibre

<b>Packaging</b>	Roll width	1.0 m	(EN 1848-1)
	Roll length	8.00 m ± 0.08 m	
Refer to current price list for packaging variations.			
<b>Appearance / Colour</b>	Top surface	Polyethylene film	
	Bottom surface	Polyethylene film	
<b>Shelf life</b>	36 months from date of production		
<b>Storage conditions</b>	The Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.		
<b>Effective thickness</b>	Effective thickness	4.0 mm ± 0.2 mm	(EN 1849-1)

## TECHNICAL INFORMATION

<b>Resistance to tear</b>	Longitudinal (MD)	150 N ± 45 N	(EN 12310-1)
	Transversal (CMD)	180 N ± 35 N	
<b>Joint shear resistance</b>	Longitudinal	550 N/50 mm ± 110 N/50 mm	(EN 12317-1)
	Transversal	300 N/50 mm ± 60 N/50 mm	
<b>Reaction to fire</b>	Class E		(EN 13501-1)
<b>Watertightness</b>	Method B: 24 hours at 60 kPa	Pass	(EN 1928)
<b>Flexibility at low temperature</b>	≤ -15 °C		(EN 1109)
<b>Maximum tensile force</b>	Longitudinal (MD)	650 N/50 mm ± 130 N/50 mm	(EN 12311-1)
	Transversal (CMD)	400 N/50 mm ± 80 N/50 mm	
<b>Elongation at maximum tensile force</b>	Longitudinal (MD)	40 % ± 15 %	(EN 12311-1)
	Transversal (CMD)	40 % ± 15 %	

## APPLICATION INFORMATION

<b>Ambient air temperature</b>	Minimum	+5 °C
	Maximum	+40 °C
<b>Relative air humidity</b>	Maximum	80 %
<b>Substrate temperature</b>	Minimum	+5 °C
	Maximum	+40 °C

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

- Guidelines and good practice for torch-applied membranes
- Method Statement - Roofing Build-up with Bituminous Membranes
- Method Statement - Bituminous membranes for below ground

## ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1 % (w/w)

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

#### SYSTEM DESIGN

Consider the following when designing the roof system:

- The supporting structure must be of sufficient structural strength to support all new and existing layers of the roof build-up.
- The complete roof system must be designed to withstand and be secured against wind uplift loadings.
- The wind uplift resistance of the adhered roofing assembly is limited by the adhesion strength of the Product to the substrate.

#### SUBSTRATE CONDITION

The substrate surface must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, laitance, oil, dust and loosely adhering particles.

### SUBSTRATE PREPARATION

#### PRIMING

##### Primer selection

Note: For information on selecting the appropriate primer, contact Sika technical service.

1. Apply the appropriate Sika® primer with the required consumption onto the prepared dry surface. Note: Refer to the individual Product Data Sheet of the primer.
2. Allow the primer to dry before membrane installation.

### APPLICATION

#### IMPORTANT

##### Unrolling at low temperatures

At low temperatures, the membrane becomes less flexible.

1. Be careful when unrolling to avoid damaging the membrane.

#### IMPORTANT

##### Damage through footwear

Footwear with spikes or sharp protrusions may puncture the membrane.

1. Use footwear with a flat profile when walking over the membrane.

#### IMPORTANT

##### Damage through overheating

The polyester reinforcement melts at +260 °C. If it is damaged through overheating, the membrane becomes unusable.

1. Keep moving the flame while torching to avoid overheating the membrane.

#### IMPORTANT

##### Reduced adhesion through insufficient heating

Make sure to heat the membrane sufficiently. If it is not sufficiently heated, the adhesion to the substrate, between layers or on the overlaps will be reduced.

1. If the membrane does not adhere to other elements, lift and retorch the unbonded areas.

##### Seasonal symbol

Note: If a seasonal symbol is printed on the roll's label, it is advisable to use the membrane during the indicated season.

##### Tackiness at high temperatures

Note: When laying the membrane at high temperatures, the integral adhesive will become 'tacky' and may restrict laying operations.

#### ALIGNMENT

#### IMPORTANT

##### Avoid coinciding joints

To avoid coinciding joints, lay the membranes parallel to one another. When applying on another bituminous membrane, make sure to straddle the overlaps of the previous layer.

1. Unroll the membrane.
2. Align the membrane.
3. Re-roll the membrane before application.

#### MEMBRANE OVERLAPS

1. Overlap the membranes by a minimum of 100 mm on the sides and 150 mm on each end.
2. At the end overlap, cut off a corner measuring 100 mm per side at an angle of 45°.
3. Weld the overlaps with great care until you see a trickle of melted mixture about 10 mm wide coming out along the line of the overlap.

#### FASTENING

When used as a roofing sheet, the membrane can be mechanically fixed to the substrate by using the correct type of fasteners.

The number of fixings, type and position depend on wind uplift forces to be resisted, pull-out strength of the fixing screws, the elastic limit of the membrane and the appropriate safety factors.

Contact Sika Technical Service for additional information.

##### Suitable substrates for fastening

- Concrete
- Wood
- Metal
- Perlite screed
- Bituminous membranes
- Coatings (check the compatibility)

#### TORCHING

1. Heat the substrate and the backing film on the underside of the membrane with a gas burner.
2. When the backing film starts to melt, the membrane is ready to stick.
3. Roll the heated membrane forward and press it firmly against the substrate to bond it.
4. Make sure a bead of melted bitumen is visible along

the full length of the overlap sides and ends when laying.

#### Suitable substrates for torching

- Concrete
- Perlite screed
- Bituminous membranes with a smooth surface
- Coatings (check the compatibility)
- Brick masonry
- Cementitious screeds

#### DETAILING

1. Use a sharp knife to cut in all details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc.

Refer to the relevant method statement for further information on detailing.

## MAINTENANCE

Check the functionality of the auxiliary works, flashings, drainage outlets, overflow pipes etc. Remove any leaves, moss and other vegetation, which could cause ponding on the roof and overload the drainage system.

To maintain the function of the roof waterproofing membrane during its lifespan, it is advisable to arrange periodically for inspection of the membrane and detailing.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Tanzania Construction Chemicals Limited

Plot No. 135  
Mbezi Industrial Area, Kinondoni  
P.O Box 7079 Dar es Salaam  
Tanzania  
Phone: +255 699 784 926



**Product Data Sheet**  
SikaShield® P55 PE RT 4 mm  
January 2025, Version 02.01  
020920011990001616

SikaShieldP55PERT4mm-en-TZ-(01-2025)-2-1.pdf