

## PRODUCT DATA SHEET

# Sika® ViscoCrete®-3088+

High range water reducing concrete admixture

### DESCRIPTION

Sika® ViscoCrete®-3088+ is a high range water reducing admixture with extended workability properties for concrete and mortar. It meets the requirements for set retarding / superplasticizing admixtures according to EN 934-2: 2001.

### USES

Sika® ViscoCrete®-3088+ is used for the production of site batched and ready mix concrete with extended workability and when required for long transport distances.

Sika® ViscoCrete®-3088+ is recommended for:

- Concrete with the highest possible water reduction (up to 30%)
- High performance concrete
- Hot weather concreting and concrete with a long transport time and/or extended workability
- High fines concrete (such as with blended cements)
- Concrete produced with very reactive cement

### CHARACTERISTICS / ADVANTAGES

Through surface absorption and sterical effects separating the binder particles, the following properties are achieved:

- Extremely powerful water reduction (thereby creating high concrete density and high strengths)
- Extends workability time while still maintaining high early strength
- Excellent plasticising effects, resulting in improved flow, placing and compaction characteristics
- Greatly improved watertightness
- Reduced creeps and shrinkage
- Reduced carbonation rate of the concrete

Sika® ViscoCrete®-3088+ does not contain chlorides or any other materials which promote the corrosion of steel reinforcement. It is therefore suitable for reinforced and pre-stressed concrete.

### APPROVALS / CERTIFICATES

Conforms to the requirements of EN 934 - 2.

### PRODUCT INFORMATION

<b>Composition</b>	Aqueous solution of modified Polycarboxylate.
<b>Packaging</b>	<ul style="list-style-type: none"> <li>▪ 1000 L IBC</li> <li>▪ 200 L Drum</li> <li>▪ 25 L Pail</li> </ul>
<b>Appearance / Colour</b>	Brown liquid.
<b>Shelf life</b>	12 months from date of production
<b>Storage conditions</b>	Store properly in an undamaged and unopened original sealed containers, in dry conditions and at temperatures between +5°C and +30°C. Protect from direct sunlight and frost.
<b>Density</b>	1.06 ± 0.02 kg/l
<b>pH-Value</b>	5 ± 1
<b>Total chloride ion content</b>	< 0.1 %

## APPLICATION INFORMATION

<b>Recommended dosage</b>	0.2 – 2.0% by weight of cement.
<b>Compatibility</b>	Sika® ViscoCrete®-3088+ may be combined with many other Sika Products. Trials must be performed before combining products in a concrete mix.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## IMPORTANT CONSIDERATIONS

When using Sika® ViscoCrete®-3088+ a suitable mix design must be selected and local material sources should be trialled.

If frozen and/or if precipitation has occurred, Sika® ViscoCrete®-3088+ may only be used after thawing slowly at room temperature and intensive mixing. Sika® ViscoCrete®-3088+ should not be added to dry cement.

Before pouring, suitability tests on the fresh concrete must be carried out.

Due to the extended workability, take special care that formwork is properly installed and secured.

## ECOLOGY, HEALTH AND SAFETY

Unmixed / mixed material must be desposed according to local regulations. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities.

Detailed health and safety information as well as detailed precautionary measures e.g. physical, toxicological and ecological data can be obtained from the Material Safety Data Sheet.

## DISPENSING

Sika® ViscoCrete®-3088+ is added to the gauging water at the plant or added on site into the concrete mixer. Allow enough time for the concrete to mix thoroughly.

The standard rules of good concreting practice, concerning production and placing, are to be followed. Refer to relevant standards.

Fresh concrete must be cured correctly.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Tanzania Construction Chemicals Limited**

Mbezi Industrial Area  
P.O Box 7079 Dar es Salaam  
Tanzania  
Phone: +255 (22) 211 3170  
mail: sales@tz.sika.com

**PRODUCT DATA SHEET**  
Sika® ViscoCrete®-3088+  
March 2021, Version 01.02  
021301011000001319

SikaViscoCrete-3088+-en-TZ-(03-2021)-1-2.pdf

