

PRODUCT DATA SHEET

SikaGrout[®]-212

General purpose high performance cementitious grout

DESCRIPTION

SikaGrout[®]-212 is a 1-component, ready to mix, free flowing, non-shrink cementitious grout.

USES

- General purpose grouting
- Machine and base plates
- Dowling reinforcing bars
- Bedding joints in pre-cast concrete sections
- Filling cavities, voids, gaps and recesses
- Post fixings

CHARACTERISTICS / ADVANTAGES

- Easy to use (ready to mix powder)
- Shrinkage compensated properties
- Pre-batched for quality
- Good flow characteristics
- Good bond to concrete
- Non-corrosive
- No segregation or bleeding
- Can be pumped or poured

PRODUCT INFORMATION

Composition	Cement, selected fillers and aggregates, special additives
Packaging	25 kg bags
Shelf life	12 months from date of production
Storage conditions	Store properly in dry conditions in undamaged and unopened original sealed packaging.
Appearance / Colour	Grey powder
Density	~2.0 kg/l (fresh density)

TECHNICAL INFORMATION

Compressive strength	3 days	7 days	28 days	(EN 196-1)
	~25 MPa	~45 MPa	~55 MPa	

APPLICATION INFORMATION

Fresh mortar density	~ 2.0 kg/l
Consumption	As a guide, ~20 kg of powder per 10 mm thickness for each m ²
Yield	1 bag yields approximately 12.5 l of mortar
Layer thickness	Minimum 10 mm/ maximum 100 mm

Ambient air temperature	+8°C min. / +30°C max.
Mixing ratio	3.25 - 3.75 litres per 25 kg bag
Substrate temperature	+8°C min. / +30°C max.
Pot Life	~20 minutes As the temperature will affect the pot life, application temperature: <ul style="list-style-type: none"> ▪ Above 73 °F (23 °C) will reduce the pot life and flow ▪ Below 73 °F (23 °C) will extend the pot life and flow

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Not to be used as an overlay in unconfined spaces
- Not to be used as a patch repair
- Refer to the Sika Method Statement for more information
- Avoid application in direct sun and/or strong wind
- Do not add water over recommended dosage
- Apply only to sound, prepared substrate
- Do not add additional water after application as this may cause cracking
- Protect freshly applied material from freezing and frost
- Keep exposed surfaces to a minimum
- Do not vibrate

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The concrete shall be thoroughly clean, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction.

MIXING

Pour the water in the recommended proportion into a suitable mixing container. While stirring slowly, add the powder to the water. Mix with low speed (< 500 rpm) hand drill mixer to avoid entraining too much air. Mix thoroughly at least for 3 minutes until homogenous with no lumps. Mix only full bags for best results.

APPLICATION

Stand the grout for ~2-3 minutes; stir with a trowel and then pour into the prepared openings. For more information on pouring techniques refer to Sika Method Statement

CURING TREATMENT

Protect the fresh material from premature drying using an appropriate curing method e.g. curing compound, moist geotextile membrane etc.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Tanzania Construction Chemicals Limited

Plot No. 135
Mbezi Industrial Area, Kinondoni
P.O Box 7079 Dar es Salaam
Tanzania
Phone: +255 699 784 926



Product Data Sheet

SikaGrout®-212
February 2024, Version 01.04
020201010010000002

SikaGrout-212-en-TZ-(02-2024)-1-4.pdf